

**DESCRIPTION:**

Penetrating Oil. Rapidly releases seizure and prevents further corrosion. 836 is an effecting multi purpose work-shop tool.

Available in Bulk and Aerosol as 736.

CHARACTERISTICS:**Corrosion Prevention**

Liquid Intelligents 836 is excellent for controlling corrosion and rust protecting metal in short term storage situations. 836 Will suppress and remove rust, corrosion and finger print smudging from steel surfaces. 836 Can be used to protect tools, outboard motors, lawn mowers, locks, hinges, parts storage etc.

Prevents Down Time

836's Viscosity uses capillary action to quickly penetrate between frozen parts softening and dissolving the corrosion bonding matrix allowing quick and easy disassembly. As exhaust specialists, panel beaters, wheel alignment, auto wreckers etc have a fixed time for each job..

Lubrication Properties

836's Capillary action allows lubrication in areas where a normal lubricants can not reach, it penetrates deep into close fitting components lubricating and freeing the surfaces. This makes 836 an extremely useful service product for maintenance engineers caretakers, ect. Liquid Intelligents 836's clear and non staining lubricating film can be used for lubricating squeaky hinges, locks, latches, pulleys, sewing machines, lawn mowers, car doors etc.

Water Displacing Fluid

836 has the ability to rapidly shift water from all surfaces and is very effective in allowing instant starts from wet when used on machinery like:-

Automobiles, jet skis, snow mobiles, motor bikes, lawn mowers, out boards etc.

Safety

Liquid Intelligents 836 contains no silicon.

Liquid Intelligents 836 will not harm, paint work, vinyl, rubber, metals.

Note:

Available in Bulk as 836 and Aerosol as 736.

Apply by: spray, dip, brush, soaking, hand sprayer and aerosol as Liquid Intelligents 735.

SERVICE BULLETIN

SPECIFICATIONS:

TEST	ASTM TEST METHOD	TEST RESULT
Density @ 15 °C kg/L	D-1298	0.843
Viscosity, cSt: @ 40 °C	D-445	9.81
Flash Point (COC), °C	D-92	70
Pour Point (COC), °C	D-97	-19
Boil Point (COC), °C	-	145 °C
Fingerprint Suppressive Action	-	Yes
Penetrating Fluid	-	Yes
Rust Protection, Cast Iron Chips RH 100%, 72 hours @ 20°C	-	Pass
Application		Drip, Spray, Dip, Brush, Aerosol
Removal	-	Petroleum Solvent,
Colour	-	Green

LIQUID INTELLIGENTS PTY LIMITED
 SYDNEY AUSTRALIA
 DISTRIBUTED BY:

